## **EUROGRIT** Aluminium Silicate

Description Eurogrit is an aluminium silicate blastcleaning grit made of coal slag from coal

fired power stations.

**Applications** Blastcleaning of steel and stone/concrete surfaces, removal of mill scale, rust, old

paint, dirt etc. Suitable for SA-3, SA-21/2 and SA-2, as well as sweep blasting (SA-

1).

**Properties** : sharp and angular Shape

: brown / black Color Hardness : 7 Mohs

: 2.4-2.6 kgs/dm<sup>3</sup> Specific density : 1.3-1.4 kgs/dm<sup>3</sup> Loose bulk density Conductivity : less than 15 mS/m Water-soluble chlorides : less than 0.001% (m/m)

SiO<sub>2</sub> **Chemical Composition** 44 -58 % in bound form. <0.1% free silica

(indication only)  $Al_2O_3$ 21 -32 %  $Fe_2O_3$ 6 12 % CaO 3 10 %  $K_2O$ 1 6 %

4 % MgO 1 0 -3 % TiO 3 % Na<sub>2</sub>O 0 -

Other : traces only

**Grain sizes** Type A1 0.2 - 0.6 mm Type AB 0.2 - 2.2 mm

Type A2 0.2 - 1.0 mm Type B1 1.2 - 2.2 mm Type A3 Type B2 0.2 - 1.4 mm 0.8 - 2.2 mm 0.5 - 2.2 mm Type X 0.5 - 1.6 mm Type B3

**Packing** 3-ply / 4-ply paper bags of 25 or 50 kg, on shrinkfoiled export pallets.

Strong woven polypropylene big bags, with 4 lifting loops.

Other packing options on request.

Quality System Certificate ISO-9001 : 2008, Certificate no. K10475/08. ISO

Product standards ISO 11126-4 and 11127.

Equipment, materials and abrasives used for surface preparation can be hazardous if used carelessly. Many national regulations exist for those materials and abrasives that are considered to be hazardous during or after use (waste management), such as free silica or carcinogenic or toxic substances. Those regulations are therefore to be observed. It is important to ensure that adequate instructions are given and that all required precautions are exercised.

TDS. 2014-Eurogrit Coalslag (UK) 1/1

## Please contact us for more information:

Worldwide

Tel: +31 (0)78 6546770 sales.eurogrit@sibelco.com Sibelco Europe

PO Box 184 NL-3350 AD Papendrecht The Netherlands

www.eurogrit.com

